

Medium	Koncentration	Stål	Rustfrit stål (V2A)	GFK	GFK HR	PE	Polymerbeton
Acetaldehyd	> 40%	-	X	-	X	-	X
Acetone		X	X	-	X	-	X
Akkumulatorsyre	> 38%	-	-	X	X	X	X
Myresyre		-	X	>30%	X	-	> 10% /B
Ammoniakvand (opløsning)		-	-	-	X	X	> 10% /B
Ammoniumhydroxid	> 30%	-	X	-	X	X	X
Batterisyre	> 38%	-	X	X	X	X	X
Benzin		X	X	-	-	-	X
Benzoesyre		-	X	X	X	X	X
Benzol		X	X	X	X	-	X
Borsyre	> 10%	-	X	X	X	X	B
Bremsevæske		X	X	X	X	X	X
Butanol	Teknisk ren	X	X	X	X	-	> 10% /B
Calciumhydroxid		X	X	X	X	X	X
Chlorbenzen		X	X	X	X	-	X
Chromsyre	> 20%	-	X	X	X	X	> 10% /B
Dichlorethylen	Teknisk ren	-	X	-	X	-	X
Dichlormethan		-	X	-	X	-	X
Dieselbrændstof		X	X	X	X	X	X
Jern-(II)-sulfat	Mættet	-	X	X	X	X	X
Jern-(III)-chlorid	Mættet	-	X	X	X	X	X
Jern-(III)-sulfat	Mættet	-	X	X	X	X	X
Eddikesyre		-	X	> 10%	X	-	> 30% /B
Ethanol		X	X	X	X	-	X
Æter		X	X	-	X	-	X
Ethylchlorid		X	-	X	X	-	X
Ethylglycol		X	X	X	X	-	X
Gearolie		X	X	X	X	-	X
Glycerin		X	X	X	X	X	X
Urinstof		-	X	X	X	X	X
Fyringsolie		X	X	X	X	X	X
Hydrazinhydrat	Vandig	-	X	X	X	X	X
Kaliumcarbonat		-	X	X	X	X	X
Kaliumchlorat		-	X	X	X	-	X
Kaliumchlorid	Vandig	-	X	X	X	X	X
Kaliumnitrat	0,5	-	X	X(vl)	X(vl)	X	X
Kaliumfosfat	> GL	-	-	X	X	X	X
Kaliumsulfat	> GL	-	-	X(vl)	X(vl)	X	X
Kerosin		X	X	X	X	-	X
Kiselsyre		-	X	X	X	X	X
Kølervæske (motorkøretøjer)		-	X	X	X	X	X
Magnesiumchlorid	Vandig	-	X	X	X	X	X
Magnesiumsulfat	Opløsning	-	X	X	X	X	X
Magnesiumnitrat	Mættet	-	X	X	X	X	X
Menthol	Fast	-	X	-	-	-	B
Methanol		X	X	-	X	-	X
Methylacrylat		-	X	-	X	-	-

Methylenchlorid		X	-	-	X	-	B
Natriumacetat		-	X	X	X	X	X
Natriumbisulfat		-	-	X	X	X	X
Natriumcarbonat		-	X	X	X	X	X
Natriumchlorid		-	X	X	X	X	X
Natriumhydrogensulfat	> GL	-	-	X	X	X	X
Natriumsulfat		-	-	X	X	X	X
Natronblegelud	> GL	-	X	-	X	-	> 5% /B
Nitrobenzen		X	X	-	X	-	X
Nitrofortynder		X	X	-	X	-	-
Oliesyre	Teknisk ren	-	X	X	X	X	B
Petroleum	Teknisk ren	X	X	X	X	-	X
Fosforsyre	> 5%	-	X	X	X	X	B
Propanol		X	X	-	X	-	X
Propionsyre		-	X	-	X	X	B
Salpetersyre	> 10%	-	X	X	X	X	B
Saltsyre	> 37%	-	-	X	X	X	-
Svovlsyre	> 78%	-	X	X	X	X	-
Svovlsyre	95%	-	X	-	X	-	-
Svovlholdig syre	Mættet	-	X	X	X	X	-
Terpentinolie		X	X	X	X	-	X
Toluol		X	-	X	X	-	X
Hydrogenperoxid	> 60%	-	X	-	X	X	-
Xylol		X	X	X	X	-	X
Citronsyre	> 10%	-	X	X	X	X	B

B = korttidsresistent indtil 72 timer

X(vl)= vandig opløsning